

TECHNICAL DATA SHEET

Date of issue: 20/06/2011

Last updating: N° 22/10/2014



SIRO S.r.l.

Via Meucci, 5 - Z.I. Selve
35037 Teolo - Padova
Tel. 049.990.11.22
Fax 049.990.15.36
e-mail: vendite@siropaints.com
www.siropaints.com

Name:	GLOSSY SIROID	Category:	high performances monocomponent paint
Definition:	Nitroalkyd enamel	V.O.C. ready to use:	660 g/l
Code:	41.1/42.1	Product outside the uses referred to 2004/42/CE	

NATURE OF THE PRODUCT

One-pack glossy enamel based on nitroalkyd resins

GENERAL USES

Product for general use, carpentry, machines tools, etc.

APPLICATION METHOD

PREPARATION OF SURFACES

The cleaning of the application surface should be total and painstaking and it is a fundamental and necessary condition to obtain positive result of the painting cycle. This means that presence of grease and oils on the surfaces, is absolutely not allowed.

Ferrous surfaces: SA2 sanding or very careful mechanical cleaning followed by degreasing using thinners. Apply a coat of primer SIRNOX N 79.2 o 79.4. When the air-drying of the primer is complete, proceed with the application of the topcoat.

PREPARATION OF THE PRODUCT

Carefully mix until an even colour and consistency are obtained. For standard airmix application dilute with our nitro thinner 07.002 or 07.001 in a percent of 30-50% to obtain a viscosity of 20"±2" Ford 4 .

APPLICATION¹

Spray gun: nozzles of 1,4-1,6 mm. diameter and 3-5 atm. pressure.

Airless. nozzle 0,09 inches, 120-150 bar

Brush/roller Only for small surfaces

TECHNICAL DATA

PRODUCT TYPE: One pack product.

**APPEARANCE²
(ASTM D 523):** glossy (88±5 gloss).

COLOURS: By request (the binder 42.1.K5 has to be used in a ratio 80/20 with the tintometric system tinters)

**SPECIFIC WEIGHT
(ISO 2811):** 1.05 ± 0.05 kg/l

**SUPPLY
VISCOSITY(DIN 53211)
:** 40"-70" Ford 4

¹ Minimum temperature for the application: + 10°C.

² With an high level of humidity and low air ventilation, the film can do a thin white layer. To prevent this is useful to add a 2-4% of thinner 07.020 inside the product before application.

TECHNICAL DATA SHEET

Date of issue: 20/06/2011

Last updating: N° 22/10/2014



SIRO S.r.l.

Via Meucci, 5 - Z.I. Selve
35037 Teolo - Padova
Tel. 049.990.11.22
Fax 049.990.15.36
e-mail: vendite@siropaints.com
www.siropaints.com

Name: **GLOSSY SIROID**

Category: **high performances
monocomponent paint**

Definition: **Nitroalkyd enamel**

V.O.C. ready to use: **660 g/l**

Code: **41.1/42.1**

Product outside the uses referred to
2004/42/CE

SOLID ON VOLUME: 42 % ($\pm 2\%$)

SOLIDS CONTENT: 45 % ($\pm 2\%$)

DRYING AT 20°C

- Dust dry:	15-20'	- Touch dry:	40'-1 hours
- Total hardening :	24 hours	- Forced drying ³	15' at 60°C
- Maximum chemical resistance: After 7 days			

RECOMMENDED COATS: One or two

THICKNESS⁴: 20-30 μ m

THEORETIC YIELD⁵: 12 m²/kg

IMPACT TEST (ASTM D 2794): 25 kg direct

ADHESION (ASTM D 3359): B= 5 on surfaces treated like above reported.

REPAINTING⁶: The product can be repainted after 1-2 hours with himself.

STORAGE STABILITY: One year stored in closed packs, in a cool, dry place, away from any sources of heat.

³ Baking the product can produce the popping effect, to avoid this is better a flash-off time of 30'-60' before put the paint to dry in the oven

⁴ Considering a dry film.

⁵ The theoretical yield has been calculated for the thickness suggested and over plane and regular surfaces.

⁶ The solvent must be completely flash-off from the film. Preliminary tests are necessary.